



Technical data

Technische gegevens
Technische Daten
Fiche technique

29-01-2015

Article P180100K33WI2, Spunb. Polyester Fleece 180 g/m²
Artikel

Composition 100% Polyester (PET)
Zusammensetzung
Samenstelling
Composition

Quality characteristic Qualitätsmerkmal Kwaliteitskenmerken Caractéristique qualitative	Technical data Technische Daten Technische gegevens Fiche technique	Test method Prüfmethode Testmethode Contrôle d'après
--	--	---

Weight	180 g/m ²	DIN EN 29073-1*
Gewicht Masse surfacique		
Thickness at 2 kPa	1,25 mm	DIN EN ISO 9073-2*
Dicke bei 2 kPa Dikte bij 2 kPa Épaisseur à 2 kPa		
Tensile Strength MD	700 N/50 mm	DIN EN 29073-3*
Höchstzugkraft Länge Trekweerstand lengte Résistance à la traction longueur		
Tensile Strength CMD	480 N/50 mm	DIN EN 29073-3*
Höchstzugkraft Breite Trekweerstand breedte Résistance à la traction largeur		
Tensile Strain at max. load MD	30 %	DIN EN 29073-3*
Höchstzugkraftdehnung Länge Rek bij breuk lengte Élongation à la rupture longueur		
Tensile Strain at max. load CMD	36 %	DIN EN 29073-3*
Höchstzugkraftdehnung Breite Rek bij breuk breedte Élongation à la rupture largeur		
Shrinkage MD	≤ 1,7 %	10 min. at 200 °C
Schrumpf Krimp Rétrécissement		
Shrinkage CMD	≤ 0,6 %	10 min. at 200 °C
Schrumpf Krimp Rétrécissement		

*in Anlehnung an die Norm / referring to standard

The data are average values and indicative.

Every user is himself responsible for testing if the product is suitable for the intended use and himself bears all associated risks and liabilities.

King Nonwovens is not liable for any damage as a consequence of unsuitable use of the product.



Tel. +31 (0) 320 232 422 • Fax. +31 (0) 320 220 630
info@kingnonwovens.nl • www.kingnonwovens.nl